

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 05-214170

(43)Date of publication of application : 24.08.1993

(51)Int.Cl. C08L 9/06
B60C 11/00
C08L 45/02
C08L 57/02

(21)Application number : 04-020146

(71)Applicant : BRIDGESTONE CORP

(22)Date of filing : 05.02.1992

(72)Inventor : SAKIYAMA ATSUSHI
MAEDA SHU
MATSUO KENJI

(54) TREAD RUBBER COMPOSITION

(57)Abstract:

PURPOSE: To provide a tread rubber composition having improved abrasion resistance and road-gripping performance.

CONSTITUTION: The objective composition is produced by compounding (A) 100 pts.wt. of a styrene-butadiene copolymer rubber containing 25-60wt.% of styrene component with (B) 10-200 pts.wt. of a resin mixture consisting of a petroleum resin composed mainly of 9C aromatic resin and a coumarone-indene resin having a softening point of <40° C, wherein the mixing ratio of the coumarone-indene resin in the resin mixture is 1-50wt.%.

LEGAL STATUS

[Date of request for examination] 08.09.1998

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 3130995

[Date of registration] 17.11.2000

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right] 27.03.2002

Copyright (C); 1998,2003 Japan Patent Office